



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 130 690 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **18.09.91** (51) Int. Cl.⁵: **A61K 9/70**

(21) Application number: **84303611.2**

(22) Date of filing: **29.05.84**

(54) **Pharmaceutical preparation for remedy of periodontal disease and process for production thereof.**

(30) Priority: **01.06.83 JP 95752/83**

(43) Date of publication of application:
09.01.85 Bulletin 85/02

(45) Publication of the grant of the patent:
18.09.91 Bulletin 91/38

(94) Designated Contracting States:
CH DE FR GB IT LI

(56) References cited:
GB-A- 1 510 999

CHEMICAL ABSTRACTS, vol. 98, part 4, 24rd
January 1983, page 337, no. 22212w, Colum-
bus, Ohio, US; M. ADDY et al.: "The develop-
ment and in vitro evaluation of acrylic strips
and dialysis tubing for local drug delivery",
J. PERIODONTOL. 1982, 53(11), 693 -9

(73) Proprietor: **TEIJIN LIMITED**
11 Minamihonmachi 1-chome Higashi-ku
Osaka-shi Osaka 541(JP)

(72) Inventor: **Suzuki, Yoshiki**
5-20-2, Tamadaira
Hino-shi Tokyo(JP)
Inventor: **Ikura, Hiroshi**
2-14-1-2-501 Shinmei
Hino-shi Tokyo(JP)
Inventor: **Noguchi, Toshihide**
3-143-508 Ekoda Nakano-ku
Tokyo(JP)
Inventor: **Izumizawa, Katsunori**
1-8-203, Shinoharanishimachi Kohoku-ku
Yokohama-shi Kanagawa-ken(JP)
Inventor: **Kinoshita, Shiro**
2-27-6-205 Tamagawa Ota-ku
Tokyo(JP)

(74) Representative: **Arthur, Bryan Edward et al**
Withers & Rogers 4 Dyer's Buildings Holborn
London EC1N 2JT(GB)

EP 0 130 690 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description**BACKGROUND OF THE INVENTION**

5 Field of the Invention

The present invention relates to a pharmaceutical preparation for remedy of periodontal disease. More particularly, the present invention relates to a pharmaceutical preparation for remedy of periodontal diseases, which is in the form of a film or sheet and is inserted in a periodontal pocket or gingiva, comprising a medicinal agent for remedy of periodontal diseases, which has medicinal actions such as a germicidal action, an antibacterial action, a plaque-dissolving action and an anti-inflammatory action, and a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, and a viscosity of 5 to 30,000mPas as determined at 20 °C with respect to a 2% aqueous solution, and also relates to a process for the production of this pharmaceutical preparation for remedy of periodontal diseases.

Description of the Prior Art

By "periodontal diseases" are meant all diseases occurring in the periodontal tissue. The main periodontal diseases are gingivitis and chronic parodontitis marginalis. Chronic parodontitis marginalis is called "pyorrhea alveolaris", and 50 to 70% of adults of thirty years and over suffer from this disease more or less. Pyorrhea alveolaris is a chronic disease of the periodontal tissue, the main complaints of which are the drainage of pus from the gingiva, the absorption of an alveolar bone, and the relaxation and tottering of teeth. It was considered that the main causes of pyorrhea alveolaris are general disorders such as hormone imbalance, abnormal metabolism, and avitaminosis but it has recently been proved that the main cause of pyorrhea alveolaris is a local inflammatory factor in the periodontal portion, which is due mainly to a plaque. The plaque is a bacterial plexus of oral bacteria, which is deposited on a groove of the tooth surface, a boundary between teeth, or a boundary between a tooth and gingiva. Inflammation is caused by bacteria in the plaque or metabolites thereof, and this inflammation extends to the deep portion to form a gingival pocket (periodontal pocket). This state is called pyorrhea alveolaris.

As the curative means, there are adopted an antiphlogistic treatment, a load relieving method, and a home curative treatment mainly for improving the affected gingival pocket and repairing the lesion of the periodontal tissue. According to the antiphlogistic treatment, the affected gingival pocket is improved by curettage of the affected gingival pocket, removal of tartar or cutting or cauterization of the gingiva, and the affected part is rendered antiphlogistic by washing and the injection of a medicine. According to the load relieving method, occlusion is adjusted, and according to the home curative treatment, teeth are cleaned and gingiva is massaged by the patient. Furthermore, there is adopted a method in which a solution of an antibacterial agent is irrigated or injected into the periodontal region and the interior of the periodontal pocket (see, for example, J.H. Hardy, H.N. Newman, J.D. Strahan; J. Clinical Periodontology, September 1982, pages 57-65). However, none of these methods have a decisive curative effect.

There has recently been reported a method in which an antibacterial agent is included in a strip composed of a water-insoluble polymeric substance such as poly(ethyl methacrylate) and the strip is placed in a periodontal pocket to kill anaerobic bacteria in the periodontal pocket [M. Addy et al.; J. Periodontol, November, 693 (1982)].

However, according to this method, since a water-insoluble polymeric substance is used, if the strip is left in the periodontal pocket, a pain or irritation is readily given to the affected part.

SUMMARY OF THE INVENTION

Accordingly, the object of the present invention is to provide a pharmaceutical preparation for remedy of periodontal diseases, which comprises a medicinal agent capable of killing bacteria and bacterial plexus in a periodontal pocket, which are fundamental causes of periodontal diseases, and of moderating inflammation, and a polymeric substance which has a flexibility such that the pharmaceutical preparation can be easily carried to the bottom of the periodontal pocket or the bottom of the gingival region as the boundary between the gingiva and teeth, such a water-solubility that, after the administration, the pharmaceutical preparation does not give an alien solid feeling causing a pain or irritation in the affected part and such physical properties that the polymeric substance is dissolved in the body fluid or exudate to form a viscous liquid which is present in the periodontal pocket or gingival region for a certain time so that the

medicinal agent is made resident in a part within the periodontal pocket or gingival region to increase the curative effect.

Another object of the present invention is to provide a process for the production of a pharmaceutical preparation for remedy of periodontal diseases.

5 Other objects and advantages of the present invention will be apparent from the following description.

In accordance with the present invention, there is provided a pharmaceutical preparation for remedy of periodontal diseases, which is in the form of a film or sheet and is inserted in a periodontal pocket or gingiva, comprising a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, and a viscosity of the 2% aqueous solution of 5 to 30,000 mPas as determined at 20 °C and a medicinal agent for remedy of periodontal diseases.

In accordance with the present invention, there is also provided a process for the production the above-mentioned pharmaceutical preparation comprising the steps of dissolving a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, and a viscosity of the 2% aqueous solution of 5 to 30,000 mPas as determined at 20 °C and a medicinal agent for remedying periodontal diseases.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

20 Research was carried out with a view to developing a pharmaceutical preparation for remedy of periodontal diseases such as pyorrhea alveolaris, having a flexibility such as facilitating the arrival of the pharmaceutical preparation at the bottom of a periodontal pocket or gingival region, being capable of retaining a medicinal agent in the pocket for a long time, and giving no pain or irritation to the affected part. As the result, it was found that this object can be attained by the above-mentioned pharmaceutical preparation which is in the form of a film or sheet and is inserted in a periodontal pocket or gingiva.

According to the present invention, a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, and a viscosity of the 2% aqueous solution of 5 to 30,000 mPas as determined at 20 °C is used as the base.

By the Young's modulus referred to in the present invention is meant the initial Young's modulus (Kg/mm²) obtained when a sheet or film having a width of 1 cm and a thickness about 0.25 mm is pulled in a tensile strength tester at a chuck distance of 2 cm. When a water-soluble polymeric substance having such a flexibility that the Young's modulus is within the above-mentioned range is used, the obtained pharmaceutical preparation has a characteristic wherein the pharmaceutical preparation is administered, it can easily be guided to the bottom of a periodontal pocket or gingival region. By the term "periodontal pocket" used herein is meant a gingival pocket, that is, a groove or clearance formed between the tooth and gingiva by periodontitis or the like. Furthermore, by the term "gingival region" is meant a groove or clearance formed in the boundary between the tooth and gingiva by artificial means or a gingival portion left after curettage of a periodontal pocket. It is preferred that the Young's modulus of the polymeric substance be 15 to 200 Kg/mm², especially 20 to 180 Kg/mm².

40 It is indispensable in the present invention that the viscosity of a 2% aqueous solution of the water-soluble polymeric substance should be 5 to 30,000 mPas as determined at 20 °C. If a water-soluble polymeric substance having a viscosity included within the above-mentioned range is used, when the pharmaceutical preparation is inserted into a periodontal pocket or gingival region, the medicinal agent can be retained at an affected part of the periodontal pocket or gingival region for a long time without flowing-out of the medicinal agent and the curative effect of the medicinal agent can be exerted at a high efficiency. It is preferred that the viscosity of the polymeric substance be 10 to 27,000 CP especially 20 to 25,000 mPas.

The base used in the present invention has the above-mentioned Young's modulus and viscosity and is a water-soluble polymeric substance having such a water solubility that is soluble in saliva or secreting fluid or exudate in the oral cavity. Since the pharmaceutical preparation of the present invention comprises this water-soluble polymeric substance, the surface portion of the preparation is dissolved by saliva or the like to some extent after administration into the periodontal pocket, and therefore, the preparation becomes adapted to the periodontal pocket or gingival region and the pain or irritation given to the affected part is moderated. This is one advantage attained by the pharmaceutical preparation of the present invention.

55 It is preferred that the degree of the water solubility be such that when the water-soluble polymeric substance is compression-molded into a disc having a weight of about 500 mg, a diameter of 13 mm and a thickness of about 3 to about 4 mm and the solubility is tested in water according to the dissolution test method of the Japanese Pharmacopoeia (the stirring speed is 200 rpm and the liquid amount is 500 ml),

more than 50% of the polymeric substance is not dissolved out within 30 minutes. When a water-soluble polymeric substance having a water solubility included within the abovementioned range, the residence property of the pharmaceutical preparation inserted in a gingival region or periodontal pocket is improved.

- Examples of the water-soluble polymeric substance are polysaccharides and derivatives thereof e.g.
- 5 lower alkyl ethers of cellulose such as methyl cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose, hydroxypropylmethyl cellulose and sodium carboxymethyl cellulose, water-soluble vinyl polymers such as polyvinyl alcohol, polyvinyl pyrrolidone, polyacrylic acid, copolymers of methacrylic acid, styrene or a vinyl type ether monomer with acrylic acid and salts thereof, and alginic acid and the salts thereof, gelatin, pullulan, starch derivatives, and polyoxyalkylenes such as high molecular weight polyethylene glycol.
 - 10 Mixtures of two or more of these water-soluble polymeric substances also can be used. Among these water-soluble polymeric substances, lower alkyl ethers of cellulose, water-soluble vinyl polymers and mixtures of two or more of them are preferred, and methyl cellulose, sodium carboxymethyl cellulose, hydroxypropyl cellulose, hydroxypropylmethyl cellulose, polyvinyl pyrrolidone, a mixture of hydroxypropyl cellulose and polyacrylic acid or a salt thereof, and a mixture of hydroxypropyl cellulose and sodium carboxymethyl
 - 15 cellulose are especially preferred. Methyl cellulose, hydroxypropyl cellulose, and a mixture of hydroxypropyl cellulose and polyacrylic acid or its salt are most preferred.

- Any of medicines effective for prevention and remedy of periodontal diseases can be used as the medicinal agent in the present invention. As the medicinal agent, there can be mentioned germicidal agents such as chlorohexidine, thimerosal, silver protein, chloramine, iodine glycerin, iodoform, boric acid, paraformaldehyde, phenol, hexylresorcinol, benzalkonium chloride, benzethonium chloride, chlorhexidine gluconate, phenododecium bromide, dequalinium chloride, cetylpyridinium chloride, and povidone iodine, antibacterial agents such as tetracycline, tetracycline hydrochloride, benzylpenicillin, ampicillin, carbenicillin, acetylkidasamycin, amoxycillin, bacitracin, cephalotin sodium, cephaloridine, cephalixin, erythromycin, chloramphenicol, oxytetracycline hydrochloride, doxycycline hydrochloride, polymyxin B sulfate,
- 25 fradiomycin sulfate, and gentamicin sulfate, plaque-dissolving agents such as lysozyme chloride, amylase, dextranase, and protease, anti-inflammatory agents such as sulpyrine, antipyrine, aspirin, phenylbutazone, meprizole, oxyphenbutazone, fenbufen, mefenamic acid, flurbiprofen, diclofenac sodium, ketoprofen, naproxen, tiaramid hydrochloride, benzydamine hydrochloride, alclofenac, ibufenac, perisoxalcite, ibuprofen, indomethacin, aluminum flufenamate, thinoridine hydrochloride, clofezone, dexamethasone, triamcinolone acetone, and prostaglandin, antihistaminic agents such as diphenhydramine hydrochloride, chlorpheniramine maleate, and clemastine, antibiotic agents such as sulfathiazole, sulfisomidine, and acetylfulratrizine, and local anesthetic agents such as ethyl aminobenzoate and tetracaine hydrochloride. Mixtures of two or more of these medicinal agents may be used. Among these medicinal agents, germicidal agents, antibacterial agents, plaque-dissolving agents, and anti-inflammatory agents are preferred.
 - 30

- 35 The amount used of the medicinal agent may be appropriately determined according to the intensity of the pharmacological activity of the medicinal agent used and the symptoms of the periodontal disease to be treated.

- The pharmaceutical preparation of the invention of this application is inserted into the periodontal pocket or gingival region, and it is administered in the form of a film or sheet. The size, shape, and thickness of the pharmaceutical preparation can be changed according to the condition of the periodontal disease to be treated and they are not particularly critical. Ordinarily, the size, shape, and thickness of the pharmaceutical preparation are changed according to the size of the periodontal pocket of the patient or the condition of the gingiva. For example, a rectangular pharmaceutical preparation having a length of 5 to 15 mm, a width of 0.5 to 2.0 mm, and a thickness of 0.1 to 0.4 mm is used for a periodontal pocket, and a
- 40
 - 45 rectangular pharmaceutical preparation having a width of 10 to 30 mm, a length of 20 to 60 mm, and a thickness of 0.1 to 0.3 mm is used for a gingival portion left after curettage of a periodontal portion.

- A plasticizer may be incorporated into the pharmaceutical preparation of the present invention according to need. As the plasticizer, there can be mentioned, for example, diethyl phthalate, dibutyl phthalate, butylphthalylbutyl glycolate, ethylene glycol, diethylene glycol, triethylene glycol, dipropylene glycol, polyethylene glycol, glycerin, and triacetin. When the plasticizer is incorporated, a pharmaceutical preparation in the form of a soft film or sheet suitable for administration into a periodontal pocket is obtained.
- 50

- Furthermore, there may be used a colorant such as a tar pigment, a taste- or smell-improving agent such as citric acid, fumaric acid, tartaric acid or menthol, and an antioxidant such as butylhydroxytoluene, propyl gallate or butylhydroxyanisole, according to need.
- 55

The pharmaceutical preparation of the present invention can be produced by dissolving the abovementioned water-soluble polymeric substance and the above-mentioned medicinal agent for remedy of periodontal diseases in a solvent, casting the obtained solution and removing the solvent by drying.

Any of these solvents capable of dissolving the respective components of the pharmaceutical preparation therein and inert to these components can be used in the present invention. For example, there can be mentioned alcohol type solvents such as methanol, ethanol, and isopropanol; ketone type solvents such as acetone and methylethyl ketone; chlorinated hydrocarbon type solvents such as methylene chloride, dichloroethane and 1,1,1-trichloroethane; and water. A mixture of two or more of these solvents can be used. An alcohol type solvent is preferred among these solvents.

It is preferred that the water-soluble polymeric substance be dissolved in the solvent in such an amount that the concentration is 3 to 50%, especially 5 to 40%, though the preferred concentration suitable for the production differs to some extent according to the molecular weight of the water-soluble polymeric substance. The medicinal agent is dissolved in an amount determined according to the intensity of the pharmacological activity of the medicinal agent. A plasticizer, a colorant, a taste- or smell-improving agent, and an antioxidant are dissolved in the solvent according to need. When the formed solution contains insoluble solids, they are removed by filtration, and it is preferred that the solution be allowed to stand still or be in vacuo for a while so that the solution is sufficiently deaerated. The solution is then cast. This casting is accomplished according to a method in which the solution is uniformly cast on a metal plate or glass plate, or by using a drum type film preparing apparatus customarily adopted in a solution casting method for production of films or an endless belt type film preparing apparatus.

Then, the solvent is removed by drying. Drying is accomplished by air-drying, standing at room temperature or heating, or according to the drying method customarily adopted in a film preparing apparatus. In view of the stability of the base and medicinal agent, it is preferred that drying be accomplished by air-drying or standing at room temperature. Thus, a pharmaceutical preparation in the form of a film or sheet is obtained. The film or sheet is cut into a desired shape. Thus, the intended pharmaceutical preparation is obtained.

Methods other than the above-mentioned method may be adopted for the production of a pharmaceutical preparation in the form of a film or sheet according to the present invention. For example, there may be adapted a calender method in which a mixture of a water-soluble polymeric substance and a medicinal agent is rolled between heated rolls to form a film or sheet, and a melt extrusion method in which a mixture of a water-soluble polymeric substance and a medicinal agent is heated and melted and the melt is extruded by a screw to form a film or sheet.

The obtained pharmaceutical preparation in the form of a film or sheet may be sterilized by heating or by ethylene oxide or radiation.

As described in detail hereinbefore, according to the present invention, a pharmaceutical preparation in the form of a film or sheet which comprises a water-soluble polymeric substance having specific Young's modulus and viscosity and a medicinal agent for remedy of periodontal diseases, and this pharmaceutical preparation has a flexibility such that it can be easily guided to the bottom of a periodontal pocket or gingival region and a property such that the medicinal agent can be retained within a local part of a periodontal pocket or gingival region and the pharmaceutical preparation moderates pains and irritations given to affected parts. Thus, excellent effects can be attained according to the present invention.

40 EXAMPLES

The present invention will now be described in detail with reference to, but is by no means limited to, the following Examples.

45 Example 1

100 g of hydroxypropyl cellulose having a viscosity of 2080 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of about 40 kg/mm² as determined at a temperature of 25 °C and relative humidity of 65% 1 g of chlorhexidine gluconate were gradually incorporated and dissolved with stirring in 1000 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, the solution was cast on a clean glass plate, and the thickness was uniformized by using a doctor knife. The cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.26 mm. The concentration of chlorhexidine gluconate in the pharmaceutical preparation was 0.98%. The Young's modulus of the film was about 40 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%.

Example 2

100 g of hydroxypropyl cellulose having a viscosity of 2080 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 48.2 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 1.0 g of chlorhexidine were gradually incorporated and dissolved with stirring into 1000 g of ethanol. The solution was allowed to stand still overnight to effect deaeration and cast on a clean glass plate. The thickness was uniformized by using a doctor knife, and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.26 mm. The concentration of chlorhexidine in the obtained pharmaceutical preparation was 0.98%.

Example 3

80 g of hydroxypropyl cellulose having a viscosity of 2080 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 48.2 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 20 g of tetracycline hydrochloride were gradually incorporated and dissolved with stirring in 960 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, and the solution was cast on a clean glass plate and the thickness was uniformized by using a doctor knife. The cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.25 mm. The concentration of tetracycline hydrochloride in the pharmaceutical preparation was 19.8%.

Example 4

100 g of hydroxypropyl cellulose having a viscosity of 200 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 39.1 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 1 g of cetyl pyridinium chloride were gradually incorporated and dissolved with stirring in 960 g of ethanol. The solution was allowed to stand still overnight to effect deaeration and cast on a clean glass sheet. The thickness was uniformized by using a doctor knife and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.27 mm. The concentration cetyl pyridinium chloride in the pharmaceutical preparation was 1.0%.

Example 5

75 g of hydroxypropyl cellulose having a viscosity of 200 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 39.1 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, 25 g of sodium polyacrylate and 10 g of amoxycillin were gradually incorporated and dissolved with stirring in 960 g of an aqueous solution of ethanol. The solution was allowed to stand still overnight to effect deaeration and cast on a clean glass plate, the thickness was uniformized by using a doctor knife, and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.28 mm. The concentration of amoxycillin in the pharmaceutical preparation was 8.5%.

Example 6

90 g of methyl cellulose having a viscosity of 4160 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 125 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 10 g of fradiomycin sulfate were incorporated and dissolved with stirring in 1000 g of ethanol, and the solution was allowed to stand still overnight to effect deaeration. The solution was cast on a clean glass plate, the thickness was uniformized by using a doctor knife, and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.20 mm. The concentration of fradiomycin sulfate in the pharmaceutical preparation was 9.8%.

Example 7

95 g of methyl cellulose having a viscosity of 4160 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 125 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 5 g of ketoprofen were gradually incorporated and dissolved with stirring in 1000 g of ethanol. The solution was allowed to stand still overnight to effect deaeration and cast on a clean glass plate. The thickness was uniformized by using a doctor knife and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.29 mm. The

EP 0 130 690 B1

concentration of ketoprofen in the pharmaceutical preparation was 4.8%.

Example 8

5 95 g of methyl cellulose having a viscosity of 9670 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 130 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 5 g of indomethacin were gradually incorporated and dissolved with stirring in 960 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, the solution was cast on a clean glass plate, and the thickness was uniformized by using a doctor knife. The cast solution was air-dried and
10 forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.25 mm. The concentration of indomethacin in the pharmaceutical preparation was 5.0%.

Example 9

15 90 g of methyl cellulose having a viscosity of 15 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 151 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%, 10 g of sodium carboxymethyl cellulose and 1 part by weight of clemastine fumarate were gradually incorporated and dissolved with stirring in 960 g of 90% aqueous ethanol. The solution was allowed to stand still overnight to effect deaeration, the solution was cast on a clean glass plate, and the thickness was
20 uniformized by using a doctor knife. The cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.30 mm. The concentration of clemastine fumarate in the pharmaceutical preparation was 1.0%.

Example 10

25 100 g of hydroxyethyl cellulose having a viscosity of 5140 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 50 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 1 g of ethyl aminobenzoate were gradually incorporated and dissolved with stirring in 960 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, cast on a clean glass
30 plate, and the thickness was uniformized by using a doctor knife. The cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.30 mm. The concentration of ethyl aminobenzoate in the pharmaceutical preparation was 0.95%.

Example 11

35 100 g of hydroxyethyl cellulose having a viscosity of 5140 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 50 kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 1 g of dequalinium chloride were gradually incorporated and dissolved with stirring in 960 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, cast on a clean glass
40 plate, and the thickness was uniformized by using a doctor knife and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film having a thickness of 0.26 mm. The concentration of dequalinium chloride in the pharmaceutical preparation was 0.95%.

Example 12

45 100 g of hydroxypropyl cellulose having a viscosity of 2080 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 48.2 kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 1.0 g of chlorhexidine gluconate were gradually incorporated and dissolved with stirring into 1000 g of water. The solution was deaerated in vacuo for 2 hrs and cast on a clean glass plate.
50 The thickness was uniformized by using a doctor knife, and the cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation on the form of a film having a thickness of 0.25 mm. The concentration of chlorhexidine in the obtained pharmaceutical preparation was 0.98%.

Example 13

55 Filmy pharmaceutical preparations prepared in Examples 1 and 2 were cut into a width of 1 mm and a length of 10 mm, and cut pieces were inserted in periodontal pockets of 10 patients suffering from pyorrhea alveolaris and the pain, drainage of pus, swelling, flare, fever, and loose feeling were checked before and

after the administration. Effects were observed in all the patients, and the pain was prominently reduced and the fever was controlled. These effects were retained for 2 to 3 days by one administration. Thus, the effectiveness of the pharmaceutical preparation of the present invention was proved.

5 Example 14

A pharmaceutical preparation in the form of a film was prepared in the same manner as described in Example 1 by using hydroxypropyl cellulose having a viscosity of 4000 mPas and a Young's modulus of 50 Kg/mm² as determined at a temperature of 25 °C, and a relative humidity of 65%, which was dissolved out
10 in an amount smaller than 10% for 30 minutes when the dissolution speed of a disc of the hydroxypropyl cellulose having a weight of 500 mg, a diameter of 13 mm, and a thickness of 3 mm, which was obtained by compression molding, was measured in water at 37 °C according to the method of the Japanese Pharmacopoeia (the stirring speed was 200 rpm and the liquid amount was 500 ml).

When this filmy pharmaceutical preparation was administered into a periodontal pocket of a patient
15 suffering from pyorrhea alveolaris, the pharmaceutical preparation was retained for a long time and the pain was prominently reduced.

Comparative Example 1

A filmy pharmaceutical preparation was prepared in the same manner as described in Example 1 by using hydroxypropyl cellulose having a viscosity of 3 mPas as determined at 20 °C (2% aqueous solution). When this preparation was administered into a periodontal pocket of a patient suffering from pyorrhea alveolaris, at the moment the top end of the preparation was inserted into the periodontal pocket, the top end portion and the portion falling in contact with an exudate became softened, and insertion of the
25 subsequent portion became difficult. Even if the preparation could be inserted, the medicinal agent retaining property was extremely poor.

In case of a filmy pharmaceutical preparation composed of sodium polyacrylate having a Young's modulus lower than 10 Kg/mm², insertion into a periodontal pocket was difficult because the preparation was too soft. In case of a filmy pharmaceutical preparation composed of polyvinyl alcohol having a Young's
30 modulus of 297 Kg/mm², a periodontal pocket was readily hurt and the pain was violent at the time of insertion because the preparation was too hard.

Comparative Example 2

Polymethyl methacrylate, a kind of a water-insoluble polymeric substance, was used as the base and dissolved in dichloromethane, and chlorhexidine gluconate was suspended in the solution. A filmy pharmaceutical preparation was produced in the same manner as described in Example 1 by using the so-obtained suspension.

When this filmy pharmaceutical preparation was administered into a periodontal pocket of a patient
40 suffering from pyorrhea alveolaris, the pain was not moderated, and the preparation was not suitable as a drug.

Example 15

95 g of hydroxypropyl cellulose having a viscosity of 2080 mPas as determined at 20 °C (2% aqueous solution) and a Young's modulus of 48.2 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and 5 g of chlorhexidine gluconate were gradually dissolved with stirring in 1000 g of ethanol. The solution was allowed to stand still overnight to effect deaeration, the solution was cast on a clear glass plate, and the thickness was uniformized by using a doctor knife. The cast solution was air-dried and forcibly dried at 40 °C to obtain a pharmaceutical preparation in the form of a film. The film was
50 cut into a width of 1 mm and a length of 10 mm. Thus, the pharmaceutical preparation in the form of a strip having a thickness of 0.3 mm and a size of 1 mm x 10 mm was obtained. As a control, the same strips containing no chlorhexidine gluconate were prepared in the same manner as mentioned above.

These strips were inserted in periodontal pockets of 5 patients with advanced periodontal diseases and
55 having at least a pair of deep pockets contralaterally in such a manner that the strips containing chlorhexidine gluconate (i.e., the present samples) were inserted into one pocket and the control samples were inserted into the other pocket. Thus, the microbiological and clinical effects of the samples were evaluated as follows:

a) Plaque Index: see Silness, J. and Løe, H.: Periodontal disease in pregnancy, II. Correlation between oral hygiene and periodontal condition. Acta Odont. Scand., 22: 121-135, 1964

b) Gingival Index: see Løe, H., and Silness, J.: Periodontal disease in pregnancy, I. Prevalence and severity. Acta Odont. Scand., 21: 121-135, 1964

5 c) Pocket Depth: The depth at which the strips are reached.

d) Bleeding: The presence (+) of bleeding is determined when the strips are inserted into the pockets or when the subgingival plaque is sampled.

The test results were obtained on 0, 2, 4, and 6 days. The results are shown in Tables 1 and 2.

Table 1 (Control side)

Patient	Age	Sex	Portion	Plaque index (day)				Gingival index				Pocket depth (mm)				Bleeding			
				0	2	4	6	0	2	4	6	0	2	4	6	0	2	4	6
A	32	f	4	1	1	1	1	2	2	2	2	6	6	6	6	+	+	+	+
B	43	m	6	3	2	1	2	2	2	2	2	10	10	10	10	+	+	+	+
C	62	m	2	2	2	2	2	2	2	2	2	5	5	5	5	+	-	+	-
D	43	m	6	2	2	2	2	2	2	2	2	6	6	6	6	+	+	+	+
E	58	m	2	1	1	1	1	2	2	2	2	7	7	7	7	+	+	-	+

Table 2 (Experimental side)

Patient	Age	Sex	Portion	Plaque index (day)				Gingival index				Pocket depth (mm)				Bleeding			
				0	2	4	6	0	2	4	6	0	2	4	6	0	2	4	6
A	32	f	4	1	1	1	1	3	3	2	2	6	6	6	5	+	+	-	
B	43	m	6	3	1	1	1	2	1	1	1	8	8	8	7	+	-	-	
C	62	m	2	2	2	1	1	2	2	1	1	5	5	4	4	+	-	-	
D	43	m	6	2	1	1	1	2	1	1	1	7	6	5	5	+	-	-	
E	58	m	2	1	1	1	1	2	2	2	2	8	7	7	7	+	-	-	

Claims

1. A pharmaceutical preparation for remedy of periodontal diseases, which is in the form of a film or sheet and is inserted in a periodontal pocket or gingiva, said pharmaceutical preparation comprising a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25° C and a relative humidity of 65%, and a viscosity of the 2% aqueous solution of 5 to 30,000 mPas as determined at 20° C and a medicinal agent for remedy of periodontal diseases.
2. A pharmaceutical preparation as claimed in claim 1, wherein the Young's modulus of the water-soluble

polymeric substance is 15 to 200 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65%.

3. A pharmaceutical preparation as claimed in claim 1, wherein the viscosity of a 2% aqueous solution of the water-soluble polymeric substance is 10 to 27,000 mPas as determined at 20 °C.
4. A pharmaceutical preparation as claimed in claim 1, wherein the water-soluble polymeric substance is a polysaccharide, a derivative thereof, a water-soluble vinyl polymer or a mixture thereof.
5. A pharmaceutical preparation as claimed in claim 4, wherein the polysaccharide or derivative thereof is at least one compound selected from the group consisting of methyl cellulose, hydroxyethyl cellulose, hydroxypropyl cellulose hydroxypropylmethyl cellulose and sodium carboxymethyl cellulose.
6. A pharmaceutical preparation as claimed in claim 4, wherein the water-soluble vinyl polymer is polyvinyl alcohol or polyvinyl pyrrolidone.
7. A pharmaceutical preparation as claimed in claim 1, wherein the water-soluble polymeric substance is a mixture of methyl cellulose, hydroxypropyl cellulose or hydroxypropyl cellulose with polyacrylic acid or a salt thereof.
8. A pharmaceutical preparation as claimed in claim 1, wherein the medicinal agent for remedy of periodontal diseases has a germicidal action, an antibacterial action, a plaque-dissolving action or an anti-inflammatory action.
9. A process for the production of a pharmaceutical preparation for remedy of periodontal diseases comprising the steps of:
 - dissolving a water-soluble polymeric substance having a Young's modulus of 10 to 250 Kg/mm² as determined at a temperature of 25 °C and a relative humidity of 65% and a viscosity of the 2% aqueous solution of 5 to 30,000 mPas as determined at 20 °C and a medicinal agent for remedy of periodontal diseases in a solvent;
 - casting the resultant solution; and
 - removing the organic solvent by drying to obtain a pharmaceutical preparation in the form of a film or sheet.
10. A process as claimed in claim 9, wherein the solvent is an alcohol type solvent.
11. A process as claimed in claim 9, wherein the removal of the organic solvent by drying is effected by air drying or allowing to stand at room temperature.

40 Revendications

1. Préparation pharmaceutique pour guérir les maladies périodontiques, qui est sous la forme d'une pellicule ou feuille et est insérée dans une poche périodontique ou gencive, ladite préparation pharmaceutique contenant une substance polymérique soluble dans l'eau, ayant un module de Young de 10 à 250 kg/mm² déterminé à une température de 25 °C et une humidité relative de 65% et une viscosité de la solution aqueuse à 2% de 5 à 30 000 mPas déterminée à 20 °C et un agent médicamenteux pour guérir les maladies périodontiques.
2. Préparation pharmaceutique selon la revendication 1, dans laquelle le module de Young de la substance polymérique soluble dans l'eau est de 15 à 200 kg/mm² déterminé à une température de 25 °C et à une humidité relative de 65%.
3. Préparation pharmaceutique selon la revendication 1, dans laquelle la viscosité d'une solution aqueuse à 2% de la substance polymérique soluble dans l'eau est de 10 à 27 000 mPas déterminée à 20 °C.
4. Préparation pharmaceutique selon la revendication 1, dans laquelle la substance polymérique soluble dans l'eau est un polysaccharide, un de ses dérivés, un polymère de vinyle soluble dans l'eau ou un de leurs mélanges.

5. Préparation pharmaceutique selon la revendication 4, dans laquelle le polysaccharide ou son dérivé est au moins un composé choisi dans le groupe constitué par la méthylcellulose, l'hydroxyéthylcellulose, l'hydroxypropylcellulose, l'hydroxypropylméthylcellulose, et la carboxyméthylcellulose sodique.
6. Préparation pharmaceutique selon la revendication 4, dans laquelle le polymère de vinyle soluble dans l'eau est l'alcool polyvinylique ou la polyvinylpyrrolidone.
7. Préparation pharmaceutique selon la revendication 1, dans laquelle la substance polymérique soluble dans l'eau est un mélange de méthylcellulose, d'hydroxypropylcellulose ou d'hydroxypropylcellulose avec un acide polyacrylique ou un de ses sels.
8. Préparation pharmaceutique selon la revendication 1, dans laquelle l'agent médicinal pour guérir les maladies périodontiques a une action germicide, une action anti-bactérienne, une action de dissolution de la plaque ou une action anti-inflammatoire.
9. Procédé de production d'une préparation pharmaceutique pour guérir les maladies périodontiques comprenant les étapes de :
dissolution d'une substance polymérique soluble dans l'eau ayant un module de Young de 10 à 250 kg/mm² déterminée à une température de 25 °C, et à une humidité relative de 65%, et une viscosité de la solution aqueuse à 2% de 5 à 30 000 mPas, déterminée à 20 °C, et un agent médicinal pour guérir les maladies périodontiques dans un solvant ;
coulage de la solution résultante ; et
enlèvement du solvant organique par séchage pour obtenir une préparation pharmaceutique sous la forme d'une pellicule ou feuille.
10. Procédé selon la revendication 9, dans lequel le solvant est un solvant du type alcool.
11. Procédé selon la revendication 9, dans lequel l'enlèvement du solvant organique par séchage se fait par séchage à l'air ou en laissant reposer à la température ambiante.

Patentansprüche

1. Pharmazeutische Zubereitung zur Heilung von Erkrankungen der Zahnwurzelhaut (periodontale Krankheiten), welche in Form einer Folie oder eines Blattes vorliegt und in eine Zahntasche bzw. die Gingiva eingelegt wird, wobei die pharmazeutische Zubereitung umfaßt: Eine wasserlösliche polymere Substanz mit einem Elastizitätsmodul von 10 bis 250 kg/mm², gemessen bei einer Temperatur von 25 °C und einer relativen Feuchtigkeit von 65 %, sowie eine Viskosität ihrer 2-%igen wässrigen Lösung von 5 bis 30.000 mPas, gemessen bei 20 °C, und einen medizinischen Wirkstoff zur Heilung von Erkrankungen der Zahnwurzelhaut.
2. Pharmazeutische Zubereitung nach Anspruch 1, bei der der Elastizitätsmodul der wasserlöslichen polymeren Substanz 15 bis 200 kg/mm² beträgt, gemessen bei einer Temperatur von 25 °C und einer relativen Feuchtigkeit von 65 %.
3. Pharmazeutische Zubereitung nach Anspruch 1, bei der die Viskosität einer 2-%igen wässrigen Lösung der wasserlöslichen polymeren Substanz 10 bis 27.000 mPas beträgt, gemessen bei 20 °C.
4. Pharmazeutische Substanz nach Anspruch 1, bei der die wasserlösliche polymere Substanz ein Polysaccharid oder ein Derivat eines Polysaccharids, ein wasserlösliches Vinylpolymer oder eine Mischung dieser Stoffe ist.
5. Pharmazeutische Zubereitung nach Anspruch 4, bei der das Polysaccharid oder dessen Derivat mindestens eine Verbindung ist, die aus der Gruppe ausgewählt ist, die besteht aus: Methylcellulose, Hydroxyethylcellulose, Hydroxypropylcellulose, Hydroxypropylmethylcellulose und Natriumcarboxymethylcellulose.
6. Pharmazeutische Zubereitung nach Anspruch 4, bei der das wasserlösliche Vinylpolymer ein Polyvinylalkohol oder Polyvinylpyrrolidon ist.

7. Pharmazeutische Zubereitung nach Anspruch 1, bei der die wasserlösliche polymere Substanz eine Mischung aus Methylcellulose, Hydroxypropylcellulose oder Hydroxypropylcellulose mit Polyacrylsäure oder einem Salz derselben ist.
- 5 8. Pharmazeutische Zubereitung nach Anspruch 1, bei der der medizinische Wirkstoff zur Heilung von Erkrankungen der Zahnwurzelhaut eine keimtötende Wirkung, eine antibakterielle Wirkung, eine plaque-lösende Wirkung oder eine entzündungshemmende Wirkung besitzt.
9. Verfahren zur Herstellung einer pharmazeutischen Zusammensetzung zur Heilung von Erkrankungen
10 der Zahnwurzelhaut, welches die (folgenden) Schritte umfaßt: eine wasserlösliche polymere Substanz mit einem Elastizitätsmodul von 10 bis 250 kg/mm², gemessen bei einer Temperatur von 25 °C und einer relativen Feuchtigkeit von 65 %, und mit einer Viskosität ihrer 2-%igen wässrigen Lösung von 5 bis 30,000 mPas, gemessen bei 20 °C, sowie ein medizinischer Wirkstoff zur Heilung von Erkrankun-
15 gen der Zahnwurzelhaut werden in einem Lösungsmittel aufgelöst; die dabei erhaltene Lösung wird ausgegossen; und das organische Lösungsmittel wird durch Trocknen entfernt, um eine pharmazeuti-
sche Zubereitung in Form einer Folie oder eines Blattes zu erhalten.
10. Verfahren nach Anspruch 9, bei dem das Lösungsmittel ein alkoholisches Lösungsmittel ist.
- 20 11. Verfahren nach Anspruch 9, bei dem das Entfernen des organischen Lösungsmittels durch Trocknen durch Lufttrocknung bewirkt wird oder durch Stehenlassen (der ausgegossenen Lösung) bei Raumtemperatur.

25

30

35

40

45

50

55